



Neoprene

# Sterile polychloroprene glove with superior chemical protection including against chemotherapy drugs

BioClean P-Zero Sterile Polychloroprene Gloves provide chemical resistance and a low particle count. They are also latex-free, powder-free and offer flexibility and comfort for the wearer enabling good dexterity.

Please contact Ansell Customer Service for specific chemotherapy drug permeation times and recommendations.

- Powder-free & latex-free
- Tested to ASTM D6978 standard
- ESD properties
- Beaded cuff for strength
- Chemical resistant
- Non-particulating EasyTear packaging



### Industries

- Controlled and Critical Environments
- Production and Manufacturing





# P-Zero BPZS

Sterile Polychloroprene Cleanroom Glove

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

	P-Zero BPZS
Material	Neoprene (Polychloroprene)
Color	Natural
Shape	Hand Specific
Cuff	Beaded
Manufacturing/QMS Audit Standards	Manufacturing QMS Audit Standards ISO 9001 PPE Regulation 2016 425 Module D
Regulatory/Standards Compliance	ASTM D6978, CE 0598, EN 420:2003 + A1:2009, EN 421:2010, EN ISO 374-1:2016, EN ISO 374-5:2016, EN 455 Part 2, Food Contact, ISO 9001:2015, Category III
Packaging	One pair per inner PE wallet; one wallet per sealed EasyTear PE pouch; 10 pouches per sealed outer PE bag; 20 outer bags per lined carton (200 pairs)
Storage	Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.
Country of Origin	Malaysia
Available sizes	6.0, 6.5, 7.0, 7.5, 8.0, 8.5, 9.0
Powder Content	Powder-Free
External Glove Surface	Textured Fingers and Palm
Sterilization Method	GAMMA irradiation (25 kGy)
Sterilization Minimum Dose	25kGy
Sterility Assurance Level	10 <sup>-6</sup>
Cleanroom Class	Class 10/ISO 4 & EU GMP Grade A
Shelf Life	Five (5) years from date of manufacture
Tested for use with Chemotherapy Drugs	Yes
Protein Level	50 µg/g or less of total extractable protein



# P-Zero BPZS

Sterile Polychloroprene Cleanroom Glove

## PHYSICAL PROPERTIES

Sizes	Typical Values							Testing Method
	6	6.5	7	7.5	8	8.5	9	
Length (mm/in)	300 / 12							EN 420
Palm Width (mm/in)	77/3	83/3.2	89/3.5	95/3.7	102/4	108/4.3	114/4.4	
Freedom from Holes	0.65 AQL Performance Level 3							EN 374-2
Typical Particle Count ≥0.5µm (counts / cm <sup>2</sup> )	<1300							IEST-RP-CC005.4
Minimum Single Wall Palm Thickness (mm/mil)	0.15 / 5.91							EN 455-2
Minimum Single Wall Finger Thickness (mm/mil)	0.18 / 7.09							EN 455-2
Minimum Single Wall Cuff Thickness (mm/mil)	0.11 / 4.33							EN 455-2
During Ageing								
Force at Break (N)	≥ 9 N							EN 455-2

## ORDERING INFORMATION

	SIZE	6	6.5	7	7.5	8	8.5	9
P-Zero BPZS	REORDER NO.	BPZS60	BPZS65	BPZS70	BPZS75	BPZS80	BPZS85	BPZS90

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

### UK

Ansell Nitritex  
T: +44 1638 663338  
F: +44 1638 668890

## Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2020 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

