

Characteristics


These low-protein, powder-free gloves eliminate air-borne particles of latex protein associated with powdered surgical gloves. Ultra-low modulus is designed for greater comfort, less hand fatigue during long surgical procedures.



**Surgical Glove
Sterile**

**DermAssist®
Powder-Free**

**Latex
Series 133**



Features:

- Textured Finish for an Improved Wet/Dry Grip
- Low Modulus for a Softer, More Comfortable Fit
- Low Protein for Reduced Chances of Latex Allergic Reactions

PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
5.5	133550	50 pairs/box, 4 boxes/case	Gloves, Surgical, Latex, Sterile, Powder-Free, Textured
6	133600	50 pairs/box, 4 boxes/case	
6.5	133650	50 pairs/box, 4 boxes/case	
7	133700	50 pairs/box, 4 boxes/case	
7.5	133750	50 pairs/box, 4 boxes/case	
8	133800	50 pairs/box, 4 boxes/case	
8.5	133850	50 pairs/box, 4 boxes/case	
9	133900	50 pairs/box, 4 boxes/case	

View this product on
our website:



Product Solutions You Trust



DermAssist®

POWDER-FREE

LATEX

SURGICAL GLOVES



DermAssist® is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D3577	Standard Specification for Rubber Surgical Gloves
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens
ASTM D5712	Standard Test Method for Analysis of Aqueous Extractable Protein in Natural Rubber

Average Length	Average Palm Thickness	Average Finger Thickness
11.6 in ♦ 295 mm	7.5 mil ♦ 0.19 mm	8.0 mil ♦ 0.20 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	30	24.5
ASTM Requirement Min. (Mpa)	24	18
Elongation (%)	1290	1150
ASTM Requirement Min. (%)	750	560



Intertek

Innovative Healthcare Corporation
 is certified to ISO 13485:2003 QMS
 for medical devices.



Product Solutions You Trust

1-800-272-1533